

BETAMATE™ 1640US

Structural Adhesives

BETAMATE™ 1640US is a one component, highly toughened epoxy based adhesive, especially developed for the body shop. The adhesive is used in the car to increase performance and body stiffness

Features and Benefits

BETAMATE™ 1640US as excellent adhesion to a variety of substrates with good tolerance to oily and dry lubes. The product helps increase the stiffness and the crash durability of the entire car body with high durability of the adhesive bond and corrosion protection. It is compatible with other mechanical and thermal joining techniques, compatible with the e-coat process and is wash resistant. It is typically used in all areas of the vehicle body structure.

Product information

Colour	Purple	
Density	1.24 g/cm ³	ISO 845

Rheological properties

Viscosity, Casson	≥80 Pa.s
-------------------	----------

Typical mechanical properties

Tensile Modulus	1800 MPa	ASTM D 638
Stress at break	32 MPa	ISO 1798
Strain at break	9 %	ISO 1798
Lap shear strength	≥32 MPa	DIN EN 1465
Peel strength, T-Peel	11 ^[2] N/mm	ISO 11339
Peel strength, Impact-Peel	38 ^[3] N/mm	ISO 11343

[1]: Tested on 1.6mm CRS

[2]: Tested on 2.0mm Aluminum

[3]: tested on 0.7mm CRS

Additional information

Adhesives

Surface Prep

The material is designed for use in the body shop area conditions where it is designed to tolerate typical oily substrates found in the body shop.

Application

All Dupont adhesives products are primarily developed in cooperation with the automobile manufacturers, according to their needs and specifications, they are approved for the specific applications as defined by the customer. The use of the product other than approved application must be released in written form by the Technical service department of DuPont Adhesives.

Application Equipment

Cartridges: hand-operated or pneumatic heated gun with mechanical piston
Drums/Pails: Pumping system with zoned heat capability



BETAMATE™ 1640US

Structural Adhesives

Application Equipment

Cartridges: hand-operated or pneumatic heated gun with mechanical piston
Drums, pails: heated pumping system

Application Parameter

The product is warm pumpable, can be applied as bead / swirl / jet spray. The ideal material temperature for conveying is >18°C.

It can be processed with the following parameters:

Application speed: up to 500 mm/s

Temperature follower plate: heated; max. 35-40°C

Temperature follower plate to doser: Per heating zone 5°C heat increase, max temperature at doser 55°C

Temperature nozzle: 45 - 65°C

For an optimum tack of the adhesive, the parts to bond should be stored at 16°C or higher.

In case of an application break longer than 30 minutes the heating of the application equipment should be switched off.

Curing Condition

Standard curing profile is 180C for 20 minutes. However the product will cure under typical body shop paint ovens and a full cure profile is available upon request

Cleaning

Uncured material can be removed with BETACLEAN 3510. In house solvents can be evaluated upon request

Delivery Form

Product is available in Drums, Pails or Cartridges

Storage Stability

Shelf life dependent upon storage temperatures of the material. Optimal storage conditions are six months at less than 25°C. For complete storage stability capabilities, please refer to Customer Test Report.



BETAMATE™ 1640US

Structural Adhesives

Revised: 2021-11-23

Page: 3 of 3

DuPont

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2022 DuPont. All rights reserved.