

# BETAMATE™ 5103-2

## Structural Adhesives

BETAMATE™ 5103-2 is a one component, epoxy-based adhesive, especially developed for the body shop. The adhesive is used in the car to increase the operation durability, crash performance and the body stiffness.

BETAMATE™ 5103-2 has excellent adhesion to automotive steels (including coated steels with good tolerance to oil and dry lubes). BETAMATE™ 5103-2 helps to increase the stiffness of the entire car body with high durability of the adhesive and adhesive bond. Due to its sealing capability metal and weld points are well protected against corrosion. It is compatible with other mechanical and thermal joining techniques, compatible with the e-coat process and precurable. Typical applications include bonding of the vehicle body structure and closure hem flange applications.

### Product information

Colour	Green <sup>[1]</sup>
Basis	Epoxy resin
Solid content	≥98 %
[1]: light green	

### Rheological properties

Extrusion Viscosity	73 <sup>[2]</sup> g/min
[2]: 25°C, Ford nozzle d=3 mm / 3 bar	

### Cure conditions

Curing time	0.5 h
Cure temperature	180 °C

### Typical mechanical properties

Tensile Modulus	6000 MPa	ISO 527-1/-2
Stress at break	51 MPa	ISO 527-1/-2
Strain at break	2 %	ISO 527-1/-2
Lap shear strength	≥22 MPa	DIN EN 1465
Peel strength, T-Peel	2.9 <sup>[4]</sup> N/mm	ISO 11339

[3]: DC01, 1.5 mm; Adhesive layer thickness 0.2 mm; Bonded area 25x10 mm

[4]: DX56D+Z100 MC, 0.8 mm; Adhesive layer thickness 0.2 mm; Bonded area 25x100 mm

### Other properties

Density	1.48 g/cm <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Storage and stability

Shelf life	3 <sup>[5]</sup> months
[5]: if storage conditions <30°C	

# BETAMATE™ 5103-2

## Structural Adhesives

### Characteristics

Compatibility

Metals

### Additional information

Adhesives

#### Surface Preparation

The material has been designed to tolerate up to 5 g/m<sup>2</sup> of surface oil.

#### Application

All Dupont T&I Adhesives products are primarily developed in co-operation with the automobile manufacturers, according to their needs and their specifications, they are approved for the specific applications as defined by the customer. The use of the product other than approved application must be released in written form by the Technical Service of DuPont T&I Adhesives.

#### Application Equipment

Cartridges: hand-operated or pneumatic gun with mechanical piston  
Drums, pails: standard pumping system

#### Application Parameter

The product is cold pumpable and can be applied as bead / swirl / stream. It can be processed with the following parameters:

Application speed: up to 500 mm/s  
Temperature follower plate: unheated  
Temperature follower plate to doser: unheated  
Temperature doser - nozzle: 30 - 50°C  
Temperature nozzle: 35 - 50°C

For an optimum tack of the adhesive, the parts to bond should be stored at 15°C or higher. In case of an application break longer than 30 minutes the heating of the application equipment should be switched off.

#### Cleaning

Uncured material can be removed with BETACLEAN™ 3510. Attention: The contact with bonded areas should be avoided.



# BETAMATE™ 5103-2

## Structural Adhesives

Revised: 2023-03-08

Page: 3 of 3

### DuPont

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

**CAUTION:** Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2022 DuPont. All rights reserved.