



BETASEAL™ U-838HV

Glass Bonding Systems

BETASEAL™ U-838HV is a one-component, fast-curing, high viscosity adhesive, which bonds primerless to most fritted glass and is suitable for direct glazed automotive glass, such as windshields, backlites, quarter glass and other stationary glass. Other uses include attaching hardware to glass and backfilling to reinstall reveal moldings or other trim. It is resistant to extended outdoor weathering without losing its adhesion and physical characteristics.

BETASEAL™ U-838HV has been crash tested to FMVSS 212. Minimum drive away time depends on temperature and humidity. Please consult fixed glass installation guide for more details.

Please contact your local DuPont sales representative for more detailed information or visit BETASEALarg.com.

Product information

Colour	Black	
Density	1.23 g/cm ³	ISO 845
Solid content	≥99 %	

Typical mechanical properties

Tensile Strength	6.5 MPa	ASTM D 412
Elongation at break	350 %	ASTM D 412
Lap shear strength, 3 days	≥4.56 MPa	DIN EN 1465
Shore A hardness	67	ASTM D 2240

Storage and stability

Shelf life	9 ^[1] months
------------	-------------------------

[1]: from date of manufacture

Additional information

Adhesives

Area of Application

All Dupont M&M adhesive products are primarily developed in co-operation with the automobile manufacturers, according to their needs and their specifications. They are approved for the specific applications as defined by the customer. The use of the product other than approved application must be released in written form by the Technical Service of DuPont M&M Adhesives.

Surface Preparation

All bonding surfaces must be free of impurities (dirt, dust, water, oil, grease, release agent and similar contaminants). BETASEAL™ U-838HV bonds primerless to most fritted glass. Primer is required for any encapsulation or areas where the adhesive bonds to paint or bare metal. See DuPont FGIG for detailed application instructions. Verify compatibility before use or consult our Technical Service or BETASEALarg.com for more information.

Application Equipment

Battery powered applicator 14.4V or greater.



BETASEAL™ U-838HV

Glass Bonding Systems

Revised: 2022-12-19

Page: 2 of 2

DuPont

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2022 DuPont. All rights reserved.